



Strengthening Method of Waste Concrete Aggregate

Ting Zhen ^{a*}

^a *School of Civil and Transportation, North China University of Water Resources and Electric Power, Zhengzhou-450045, Henan, China.*

Author's contribution

The sole author designed, analysed, interpreted and prepared the manuscript.

Article Information

DOI: <https://doi.org/10.9734/air/2024/v25i51133>

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/121670>

Review Article

Received: 17/06/2024

Accepted: 20/08/2024

Published: 23/08/2024

ABSTRACT

After the construction solid waste is broken, it is directly used as recycled aggregate, which often has the disadvantages of large porosity, high water absorption and low strength, resulting in low strength and poor durability of the recycled concrete prepared by it. Therefore, the effective use of recycled aggregate in concrete is limited. For this reason, researchers have carried out systematic research on the modification of recycled aggregate in order to realize the reuse of resources. The research shows that the strengthening methods of recycled aggregate can be divided into physical methods, chemical methods and microbial methods to make up for the defects of recycled aggregate. In this paper, the concrete content of recycled aggregate strengthening method is reviewed, which provides some theoretical support for the treatment of construction waste and its utilization as recycled aggregate.

Keywords: *Recycled aggregate; physical strengthening; chemical strengthening; microbial enhancement.*

*Corresponding author: E-mail: 2953478267@qq.com;

1. INTRODUCTION

As one of the essential materials in civil engineering, concrete is widely used in urban construction, transportation infrastructure construction and other fields. If only natural stone is used to produce concrete, excessive mining of sand and stone is bound to cause serious damage to the ecological environment. At the same time, a large number of old houses are demolished, and construction waste cannot be effectively dealt with, thus causing serious problems [1,2]. The development of recycled concrete aggregate recycling can not only provide treatment for construction waste, but also alleviate the pressure of natural aggregate shortage. However, compared with natural aggregates, recycled aggregates have the characteristics of low apparent density, high porosity, rough surface, high water absorption, high crushing value, and more micro-cracks, all of which are caused by the presence of adhesive old mortar [1,3,4]. In addition, recycled concrete also has some disadvantages such as large water consumption, large shrinkage, poor mechanical properties and limited durability [5,6,7,8]. These disadvantages greatly limit the application of recycled concrete in practical engineering.

How to strengthen the construction waste as a recycled aggregate to completely or partially replace the natural aggregate such as sand and stone to produce concrete, the key is to strengthen the treatment of recycled aggregate. At present, the strengthening method of recycled aggregate has become a hot topic in the research of recycled aggregate. Therefore, in this paper, the strengthening methods and existing problems of recycled aggregate are reviewed and summarized.

2. RECYCLED AGGREGATE TREATMENT METHODS

2.1 Physical Strengthening

Physical strengthening, as the most commonly used method, relies on mechanical equipment to polish the broken recycled aggregate, so that the collision and friction between the aggregate and the aggregate or between the aggregate and the mechanical equipment can remove the mortar attached to the surface of the recycled aggregate and excessive corners, so that the appearance of the recycled aggregate is closer to the natural aggregate.

The heating grinding method developed by Japan Sanling Company [9] first heats the recycled coarse aggregate that is simply broken and the particle size is less than 40 mm to more than 300°C, so that the cement mortar attached to the surface of the recycled aggregate is dehydrated and embrittled, and then the recycled coarse aggregate treated at high temperature is put into the grinding equipment to effectively remove the old mortar on the surface of the aggregate. There are also the vertical eccentric device grinding method [10,11,12] proposed by Takenaka Works Shop in Japan and the horizontal mechanical forced grinding method [13,14] developed by Pacific Cement Co., LTD., both of which enable the recycled coarse aggregate to grind off the mortar under the action of high-speed rotating eccentric wheel and wear-resistant lining plate, thus strengthening the recycled coarse aggregate.

Kathy Bru et al. [15] used microwave heating to treat the reclaimed aggregate and finally obtained the sample with low fracture energy. Drawing on foreign experience, Professor Li Qiuyi from Qingdao University of Technology proposed particle shaping technology, which uses a high-speed rotating spreader plate to drive the high-speed movement of aggregate and produce centrifugal effect. Through the collision and friction between aggregate and machinery or between aggregate and aggregate, the mortar layer on the surface of aggregate is automatically peeled off, eliminating excess edges and corners, and getting better grain shape. Reclaimed coarse aggregate with low water absorption and crushing index is an effective physical strengthening method at present in China. Ma [16] used heating method to treat building waste concrete and obtained recycled aggregate with good quality. Russian research shows that the modified treatment of recycled coarse aggregate by ball mill can reduce crushing index and water absorption, and improve the quality of recycled coarse aggregate [17].

However, it is undeniable that physical strengthening methods usually consume energy and cost more, and are easy to cause the formation of micro-cracks inside the recycled aggregate, causing physical damage.

2.2 Chemical Strengthening

The chemical method uses chemical solution to spray, soak and dry the recycled coarse

aggregate, so that a substance in the chemical solution reacts with a substance in the recycled aggregate, removes the attached mortar, or fills and repair the voids and micro-cracks of the recycled coarse aggregate, reduces the porosity of the aggregate and improves the strength of the aggregate.

① Polymer emulsion treatment

Polymer emulsion treatment is to soak or spray recycled aggregate by taking advantage of the polymer emulsion's good adhesion and hydrophobicity, and can be cured and formed in a short time. Polymer molecules can quickly fill the micro-cracks inside the recycled aggregate and the micro-pores attached to the hardened cement mortar, and at the same time form a dense impervious film on the surface of the recycled aggregate. Thus, the water absorption of recycled aggregate is reduced.

When regenerated aggregate is impregnated with PVA, Kou et al. [18] fill the pores attached to hardened cement mortar with PVA molecules, densify its structure and reduce its porosity, which can greatly reduce the water absorption rate of regenerated aggregate [19]. Wang Fuxing [20] showed that the water absorption of reclaimed fine aggregate modified by PVA decreased by 58.3%, while the effect of VAE emulsion was not obvious. Both Tsuiino [21] and Spaeth [22] modified reclaimed aggregates with silane polymer could reduce the water absorption of reclaimed aggregates, but the reduction effect was related to the type of polymer. Xiao Kaitao [23] treated recycled aggregate with polymer solution and organic waterproofing agent, resulting in a decrease in 24h water absorption of 57% and 74%, respectively. Shi-Cong Kou et al. [18] impregnated recycled aggregates with polyvinyl alcohol, which improved the mechanical properties and chloride ion penetration resistance of recycled concrete.

② Acid treatment

The regenerated aggregate is soaked in acid solution (such as CH_3COOH , H_3PO_4 , HCl , H_2CO_4), and the acid solution is used to chemically react with the hardened cement mortar (CaO , Al_2O_3 , Fe_2O_3 , etc.) attached to the surface of the regenerated aggregate to peel the hardened cement mortar and improve the surface morphology of the particles.

Tam et al. [24] used HCl , H_2SO_4 and H_3PO_4 to soak the recycled aggregate, all of which could reduce the content of adhesive hardened cement mortar on the surface of the recycled aggregate, thus reducing the water absorption. Purushothaman et al. [25] treated the reclaimed coarse aggregate with HCl , H_2SO_4 , scrubs and heating washing, and found that the reclaimed coarse aggregate obtained by H_2SO_4 treatment and heating washing treatment had a low water absorption rate, and other properties were similar to those of natural coarse aggregate. The strength of recycled aggregate concrete is very close to that of natural aggregate concrete. Soren et al. [26] studied 5 kinds of strengthening methods for recycled coarse aggregate, and found that soaking with 5% dilute HCl solution improved the water absorption of recycled coarse aggregate significantly, and the crushing value decreased less. Wang Jianghao et al. [27] used H_2CO_4 solution and HCl solution to treat recycled coarse aggregate by chemical leaching, which could effectively remove the adhesion of hardened cement mortar on the surface of recycled coarse aggregate and reduce water absorption. Ha-Seog Kim et al. [28] used sulfuric acid and hydrochloric acid to remove the adhesive mortar on the surface of recycled aggregate to reduce the water absorption of recycled aggregate.

③ Treatment of volcanic ash slurry

Pozzolanic slurry treatment method is a modified and strengthened treatment method based on pozzolanic slurry reaction. When active powder slurry such as fly ash silica fume and diatomite is used to treat recycled aggregate, the hardened cement mortar attached to the surface of recycled aggregate can stimulate the pozzolanic effect of the active powder and the micro-aggregate filling effect, and fill the micro-cracks inside the recycled aggregate and the micro-pores in the surface hardened cement mortar. Reduce porosity.

Katz [29] applied ultrasonic cleaning and wollastonite slurry soaking to treat recycled aggregate, and found that the soaking treatment with wollastonite slurry had a significant improvement effect. Tam [30,31] et al. used pure cement slurry and cement plus silica slurry to treat recycled aggregate, and found that both can improve the structure of attached slurry and the transition zone of the old interface. After adding silica ash, the structure of recycled aggregate and the transition zone of the new and old

interface become denser, and the effect is better. Zhang Xuebing et al. [32], [33] used active powder cement slurry and slurry containing homogeneous distribution of ultra-fine particle dense system to soak and encapsulate recycled coarse aggregate, both of which could reduce the crushing index of recycled coarse aggregate, enhance the density of interfacial transition zone, improve the strength, and RPC slurry had better strengthening effect. Sun Yuedong et al. [34] modified recycled aggregate with 4 different chemical grout. Fan Xiaoping et al. [35] found in the experimental study that adding 12%UEA expansion agent, 5% inorganic aluminum salt composite waterproofing agent and 10% silica ash to pure cement slurry and cement slurry respectively had different soaking effects on recycled aggregate, and concluded that inorganic composite solution had the best soaking effect. Du Ting et al. [36] also found through the test that adding Kim powder, silica powder and grade fly ash to pure cement slurry and cement slurry respectively had different soaking and strengthening effects on recycled aggregate. According to the conclusion, adding Kim powder slurry to cement has obvious improvement effect on recycled coarse aggregate and is better than the other three kinds of slurry.

④ Water glass solution treatment

Water glass solution treatment method refers to the reaction of water glass solution with calcium hydroxide to generate C-S-H and silicic acid gel, fill the micro-cracks inside the recycled aggregate and the micro-pores attached to the hardened cement mortar on the surface of the recycled aggregate, solidifying the hardened cement mortar attached to the surface of the recycled aggregate [37], so as to refine the pore size, reduce the porosity and reduce the water absorption rate. In addition, the water glass solution treatment method can also wash the dust, mud and impurities attached to the surface of the recycled aggregate, and has the modification effect of wet treatment.

Guo Qijie et al. [38] used water glass solution, silicone resin and silane coupling agent to soak recycled aggregate, and the performance of recycled aggregate after treatment was improved to varying degrees, among which the treatment effect was best when the concentration of water glass solution was 30% and the temperature was 180°C. Yang Feihua et al. [39] showed that when

3% water glass solution was soaked for 1h at room temperature, the 7d, 28d and 60d compressive strength of recycled concrete prepared with recycled aggregate was increased by 30.6%, 27.1% and 17.8% respectively, indicating a large increase. Cheng Haili et al. [40] [41] studied the effect of sodium silicate solution concentration and soaking time on the modification and strengthening of recycled aggregate. It is found that the strength of recycled concrete prepared with recycled aggregate can be significantly improved by soaking water glass solution with 5% concentration for 1h. However, when the recycled aggregate is soaked in high concentration and for a long time, it will affect the strength of recycled concrete, and the influence mechanism is not clear.

⑤ Carbonization treatment

Carbonization reaction modification treatment of regenerated aggregate is based on carbonization reaction, using the surface of regenerated aggregate to attach $\text{Ca}(\text{OH})_2$ and C-S-H in hardened cement mortar with CO_2 , and the resulting CaCO_3 crystal and silicic acid gel to fill the internal micro-cracks of aggregate and attach the hardened cement mortar micro-pores, so that the overall structure of regenerated aggregate becomes dense. Thus, porosity is reduced, water absorption of recycled aggregate is reduced, and strength is improved [42].

Kou et al. [43] studied the effect of carbonization treatment on regenerated aggregate with 100% CO_2 concentration and reaction time as a variable in the test. The research shows that the application of CO_2 can improve the physical properties of recycled aggregate, and with the extension of curing time, the more full the degree of carbonization, the greater the improvement of the performance of recycled aggregate, the higher the quality of aggregate. Pan Ganghua et al. [43] invented a method to strengthen recycled concrete fine aggregate by carbonizing carbon dioxide. Compared with untreated recycled fine aggregate, the water absorption rate was reduced by nearly 53% and the crushing value was reduced by nearly 45% [44]. Li Yake [45] adopted CO_2 to strengthen the treatment of reclaimed fine aggregate, which can effectively improve the apparent density, reduce the water absorption rate and crushing index, and make the performance of reclaimed fine aggregate after

treatment more similar to that of natural fine aggregate.

2.3 Microbial Enhancement

Microbial method is to promote the precipitation of calcium carbonate in different environments by the biological control and induction process of microorganisms to make up for the defects of recycled aggregates.

Singh et al. [46] studied the strengthening effect of ureahydrotic bacteria and non-ureahydrotic bacteria on recycled aggregate, and the results showed that both of the above two bacteria could improve the performance of recycled aggregate, among which *Bacillus ureahydrotic* showed better mineralization potential, which once again verified the characteristics of ureahydrotic microorganisms with fast reaction and high efficiency. Salman Rais et al. [47] used microbial mineralization technology to explore the impact on the performance of recycled aggregate concrete, and found that calcium carbonate precipitation generated by MICP technology can fill the internal pores and holes of concrete to make its structure more dense, and thus significantly improve its strength, durability and other properties. In summary, microbial mineralization deposition technology is a feasible method that is expected to achieve ecological friendliness, but this method is greatly affected by conditions and is still in the experimental test stage, requiring further research.

3. CONCLUSIONS

The current strengthening methods have relatively obvious effects on the recycling of recycled aggregate. Although there are advantages and disadvantages in the strengthening process, it is undeniable that these strengthening technologies provide strong technical support for the utilization of recycled aggregate. Relatively speaking, it has good results and application prospects for the strengthening of adhesive mortar on aggregate surface. Relatively speaking, it has good results and application prospects for the strengthening of adhesive mortar on aggregate surface. In this kind of strengthening method, after the treatment of aggregate by volcanic ash slurry, the aggregate performance improvement effect is relatively good, the operation is simple, the cost is saved, and the secondary pollution will not be caused in the process.

4. SUMMARY

The current research mainly focuses on the improvement of a single strengthening method, and there are few studies on two or more methods of compound strengthening recycled aggregates. Therefore, how to use appropriate strengthening methods to strengthen aggregates, so that the performance of aggregates can reach or even exceed that of natural aggregates, so as to solve the shortage of natural aggregates and the phenomenon of wanton landfill of construction waste. It is still one of the problems that concrete workers need to pay attention to.

In addition, the design mix ratio of recycled aggregate concrete must be prepared before construction, and the reasonable design of the mix ratio of concrete can ensure that the structure can withstand the design load and maintain stability and safety during its service life. Secondly, the cost of pretreatment of recycled aggregate and the cost of natural aggregate should be balanced to achieve the win-win effect of saving cost and improving the utilization rate of recycled aggregate.

DISCLAIMER (ARTIFICIAL INTELLIGENCE)

Author(s) hereby declare that NO generative AI technologies such as Large Language Models (ChatGPT, COPILOT, etc) and text-to-image generators have been used during writing or editing of manuscripts.

COMPETING INTERESTS

Author has declared that no competing interests exist.

REFERENCES

1. X.P. Li, Recycling and reuse of waste concrete in China Part I. Material behaviour of recycled aggregate concrete, *Resour. Conser. Recycl.* 2008;53: 36–44.
2. Zheng L, Wu HY, Zhang H, Duan HB, Wang JY, Jiang WP, Dong BQ, Liu G, Zuo J, Song QB. Characterizing the generation and flows of construction and demolition waste in China, *Constr. Build. Mater.* 2017;136:405–413.

3. Ying JW, Meng QJ, Xiao JZ. Effect of CO₂-modified recycled aggregate on compressive strength of concrete, *J. Build. Mater.* 2017;20:277–282.
4. Thomas C, Setién J, Polanco JA. Structural recycled aggregate concrete made with precast wastes, *Constr. Build. Mater.* 2016;114:536–546.
5. Poon CS, Shui ZH, Lam L, Fok H, Kou SC. Influence of moisture states of natural and recycled aggregates on the slump and compressive strength of concrete, *Cem. Concr. Res.* 2004;34:31–36.
6. Abdalhmud JM, Ashour AF, Sheehan T. Long-term drying shrinkage of self compacting concrete: Experimental and analytical investigations, *Constr. Build. Mater.* 2019;202:825–837.
7. Zhang HR, Ji T, Zeng XP, Yang ZX, Lin XJ, Liang YN. Mechanical behavior of ultra-high performance concrete (UHPC) using recycled fine aggregate cured under different conditions and the mechanism based on integrated microstructural parameters, *Constr. Build. Mater.* 2018;192:489–507.
8. Kazemian F, Rooholamini H, Hassani A. Mechanical and fracture properties of concrete containing treated and untreated recycled concrete aggregates, *Constr. Build. Mater.* 2019;209:690–700.
9. Tatsuyashiki H, Bulk H, Koga Y. et al. Acceptable properties of highly treated recycled aggregate recovered from high-strength concrete using various cements, 2nd Report, *Material Construction.* 2002;1019-1020.
10. Huang Qi, Shi Xiaoshuang, Wang Qingyuan, et al. Recycled coarse aggregate on the properties of fly ash base polymer concrete carbonation effect [J]. *Journal of silicate bulletin*, 2015, (5) : 1264-1269 + 1281.
DOI: 10.16552 / j.carol carroll nki issn1001-1625.2015.05.016.
11. Kudo T, Kudo K, Bulk H, Shimizu N. A practical study on the influence of adhered mortar on the quality of recycled aggregate. *Proceedings of the Architectural Institute of Japan.* 1997;1095-1102.
12. Horiuchi K, Shimizu I, Tanaka H. Quality improvement effect of recycled aggregate by advanced treatment. *Japan Society for Construction Science and Technology Gak Technical Lecture Collection.* 1999;143-144.
13. Takahashi YK, Tanka KK, Takeuchi HY. Investigation on the factors affecting the properties of recycled aggregate concrete. *Journal of the Architectural Institute of Japan Structural Engineering.* 2011; 76(659):9-14.
14. Tateyashiki H, Takeshi H, Sugiyama N, et al. Properties of highly treated recycled aggregate recovered from high-strength concrete using various types of cement: Properties of recycled aggregate by the heat rubbing method [J]. *Materials Construction.* 2001;777-778.
15. Kathy Bru, Solène Touze, Florent Bougeois, et al. Assessment of a microwave- assisted recycling process for the recovery of high -quality aggregates from concrete waste[J]. *International Journal of Mineral Processing.* 2014;126: 90-98.
16. Ma XW, Han ZX, Li XY, Meng FL. Thermal treatment of waste concrete and the rehydration properties of the dehydrated cement paste. *Journal of Qingdao Technological University.* 2009,30(4):93-97.
17. Wang F. Experimental study on preparation technology and main properties of recycled concrete [D]. *Northeast Petroleum University;* 2010.
18. Shi-Cong Kou, Chi-Sun Poon. Properties of concrete prepared with PVA-impregnated recycled concrete aggregates[J], *Cement & Concrete Composites.* 2010;32:649-654.
19. Shi CK, Chi SP. Properties of concrete prepared with PVA-impregnated recycled concrete aggregates. *Cement and Concrete Composites.* 2010;8(32):649-654.
20. Wang Fuxing. Research on surface modification of recycled aggregate from construction waste and its effect on mortar properties. *Jinan University;* 2015.
21. Tsujino M, Noguchi T, Tamura M, et al. Application of conventionally recycled coarse aggregate to concrete structure by surface modification treatment. *Journal of Advanced Concrete Technology.* 2007;5 (1):13-25.
22. Spaeth V, Djerbi Tegger A. Improvement of recycled concrete aggregate properties

- by polymertreatments1. Intemational Journal of Sustainable Built Environment. 2013;2(2):143-152.
23. Xiao Kaitao. Research on the properties of recycled concrete and its modification [D]. Wuhan University of Technology; 2004.
 24. Vivian WY, Tam CM, Tam KNLe. Removal of cement mortar remains from recycled aggregate using pre-soaking approaches1.Resources Conservation and Recycling. 2007;50(1):82-101
 25. Purushothaman R, Amirthavalli RR, Karan L. Influence of Treatment Methods on the Strengthand Performance Characteristics of Recycled Aggregate Concrete. Journal of Materials inCivil Engineering. 2014;27(5):1-7.
 26. Solon, Peng Peng, ZHAO Yanru. Experimental study on the reinforcement of recycled coarse aggregate[J]. Materials Herald. 2015;29(25):362-365.
 27. Wang Jianghai, Geng Ou, LI Fumin. Experiment on the effect of multiple modification methods of recycled coarse aggregate on the improvement of concrete compressive strength[J]. Journal of Building Science and Engineering. 2016;33(2):91-97.
 28. Ha-Seog Kim, Byoungil Kim, Kee-Seog Kim, et al. Quality improvement of recycled ageregates using theacid treatment method and the strength characteristics of the resulting mortarf]. Journal of Material Cyclesand Waste Management. 2016;19:968-976.
 29. Katz A. Treatments for the improvement of recycled aggregate1. Journal of Materials in Civil Engineering. 2004;16(6): 597-603.
 30. Vivian WY, Tam XF, Gao CM. Tam Microstructural analysis of recycled aggregate concreteproduced from two-stage mixing approach[1]. Cement and Concrete Research, 2005;35(6):1195-1203.
 31. Vivian WY, Tam CM, Tam. Diversifying two-stage mixing approach (TSMa) for recycledaggregate concrete: TSMAs and TSMAsc[1]. Construction and Building Materials. 2008;22(10)2068-2077.
 32. Zhang XB, Wang GQ, Fang CZ, et al. Effect of RPC reinforced aggregate admixture on the strength of recycled concrete[. Journal of Construction Materials. 2015;18(3):400-408.
 33. Zhang XB,Fang Z,Guo XY, et al. Strength and damage mechanism analysis of recycled aggregate concrete strengthened and pretreated by DSP[. Industrial Building. 2012;42(4):15-20.
 34. Sun Yedong, Wang Tao. Influence of recycled aggregate reinforcement on the basic mechanical properties of recycled concrete. Sichuan Research on Building Science.2010;36 (4):212-215.
 35. Xiaoping FAN, Yinfang XU. Strengthening test of recycled aggregate[J]. Shanghai Building Materials. 2005;4:22-23.
 36. Ting DU, LI Hui-Qiang, Xian-Guo WU. Reinforcement test of recycled aggregates in concrete[J]. New Building Materials. 2002;3:6-8.
 37. Shayan A, Xu A. Perfomance and properties of' structural concrete made with recycled concreteaggregate[. ACI Materials Journal. 2003;100(5)
 38. Guo Qijie. Research on reinforced treatment of recycled aggregate and its application in asphalt stabilised crushed stone [D]. Chang'an University; 2014.
 39. YANG Feihua, HAO Liwei, CHENG Haili. Experimental study on the effect of water glass modified waste concrete recycled coarse aggregate on concrete strength and frost resistance [. Jiangxi building materials,2015,165(12):43-45.
 40. Cheng Haili. Experimental study on strengthening of water glass on concrete recycled aggregate[J]. New Building Materials. 2005;(12):12-14.
 41. CHENG Haili,ZHANG Di. Frost resistance and erosion resistance of water glass reinforced recycled aggregate concrete[J]. New Building Materials. 2008(8):5-7.
 42. Groves GW, Brough A, Richardson IG, et al. Progressive changes in the structure of hardenedCS cement pastes due to carbonation[J]. Journal of the American Ceramic Society. 1991;74(11): 2891-2896.
 43. Castellote M, Fern L, Kou S C, Andrade, et al. Chemical changes and phase analysis of OP Cpastes carbonated at different CO2 concentrations[J]. Materials and structures. 2009;42(4):515-525.
 44. Papadakis V G, Vayenas, Fardis. Fundamental modeling and experimental

- investigation of concrete carbonation[J]. ACI Materials Journal. 1991;88(4).
45. Li YK. Research on carbon dioxide reinforced recycled aggregate to improve its performance [D]. Hunan University; 2014.
46. Singh LP, Bisht V, Aswathy MS, et al. Construction and Building Materials. 2018;181:217.
47. Salman Rais M, Ahmad Khan R. Construction and Building Materials. 2021; 290:23280.

Disclaimer/Publisher's Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of the publisher and/or the editor(s). This publisher and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.

© Copyright (2024): Author(s). The licensee is the journal publisher. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:

The peer review history for this paper can be accessed here:

<https://www.sdiarticle5.com/review-history/121670>