



Physico-chemical Characterization of Biochar from Different Biomass Materials

R. Diya ^{a++*}, A. V. Meera ^{b#*}, B. Rani ^{a†}, N. Leno ^{a#}
and J. John ^{b†}

^a Department of Soil science and Agricultural Chemistry, College of Agriculture, Vellayani, 695522, Thiruvananthapuram, India.

^b Integrated Farming System Research Station (KAU), Karamana, 695002, Thiruvananthapuram, India.

Authors' contributions

This work was carried out in collaboration among all authors. All authors read and approved the final manuscript.

Article Information

DOI: 10.9734/IJECC/2023/v13i113446

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/109065>

Original Research Article

Received: 01/09/2023

Accepted: 06/11/2023

Published: 11/11/2023

ABSTRACT

Aim: To conduct the physico-chemical analysis of biochar derived from various organic residues, an examination of the physical characteristics including bulk density, water retention capacity, and the chemical properties such as pH, electrical conductivity, cation exchange capacity, total organic carbon, as well as the concentration of macro and micro nutrients were evaluated.

Study Design: Experiment was conducted in completely randomized design with 7 treatments and 3 replications.

Place and Duration of Study: The investigation was conducted at Integrated Farming System Research, Karamana, Kerala Agricultural University during 2021-2023.

Methods: Organic residues from different sources were converted into biochar utilizing a double barrel *Biochar Kiln*, and subsequently, the biochars were analyzed in a Soil and Plant Analysis laboratory to determine their physical and chemical properties.

⁺⁺ PG Scholar;

[#] Assistant professor;

[†] Professor and Head;

*Corresponding author: E-mail: meera.av@kau.in, diya-2021-11-051@student.kau.in;

Result: Physio-chemical properties of biochar vary significantly with the choice of feedstock material. Banana pseudostem biochar reported the lowest bulk density (0.21 Mg m^{-3}) and highest water holding capacity (327.74%). All the biochar produced were alkaline in nature, and they contained high cation exchange capacity ranging between 9.34 to $14.10 \text{ cmol (+) kg}^{-1}$. Macro and micro nutrient contents were comparatively higher in *Limnocharis flava* biochar and Banana pseudostem biochar.

Conclusion: Organic residues can be successfully converted to biochar and results obtained show the suitability of application of produced biochar as a soil amendment.

Keywords: Biochar; pyrolysis; organic residue; physico-chemical properties.

1. INTRODUCTION

The plethora of farming methods has led to a notable escalation in the quantity of agricultural goods produced, consequently contributing to a general surge in the generation of organic waste and the ensuing contamination of the ecosystem. The indiscriminate incineration of these remnants has led to numerous ecological hazards, including substantial dispersal of particles in the air and the release of gases that contribute to the greenhouse effect [1]. It has been reported that the combustion of 116.3 Teragrams (Tg) of agricultural remains resulted in the emission of approximately 176.1 Tg of carbon dioxide, 10 Tg of carbon monoxide, 313.9 Gigagrams (Gg) of methane, 8.14 Gg of nitrous oxide, and 151.14 Gg of ammonia [2]. The potential ramifications of these consequences hold the capacity to impact the overall composition of the Earth's atmosphere as well as the chemical makeup of the environment. An imperative requirement of the present moment is the implementation of an efficacious and proficient management plan for the handling of organic waste. The significance of biochar applications in agricultural production systems is increasingly being recognized due to the economic and environmental advantages it offers [3] and it has been demonstrated to serve as a viable alternative approach for managing agricultural waste [4].

Biochar is a substance that contains a high level of carbon and is formed through the process of burning organic materials in the presence of restricted supply of oxygen. It exhibits a strong resistance to microbial decay and possesses remarkable capacity to sequester carbon in the soil for extended periods of time, often spanning centuries to millennia. Notably, the discharge of greenhouse gases, such as carbon dioxide and methane, from the atmosphere can be notably diminished [5]. The recalcitrance of the substance arises from its aromatic composition [6] and the presence of a crystalline graphing

sheet within its structure. In comparison to organic matter, the substance exhibits a significantly prolonged period of recalcitrance within the soil, spanning 10-1000 times longer [7]. Biochar application has benefits such as soil carbon sequestration [8], an amendment to improve soil fertility [9] and for remediation of contaminated soils [10]. Biochar characteristics, such as nutrient composition, are ascertained by the initial source material, while the stability of biochar is primarily affected by the conditions under which it is produced. In general, biochar prepared from manure are nutrient rich followed by grasses and then wood [11]. Pyrolysis temperature for biochar production generally ranges between 300 to 1000 °C [12]. But slow pyrolysis carried out at temperature range between 300 to 700 °C yields more biochar [13] and have desirable properties such as high porosity, carbon rich product, and aromatic surfaces [14].

Biochar serves as a soil conditioner, enhancing various physical and chemical properties of soil, including its ability to retain water, its specific surface area, porosity, aggregation [15], cation exchange capacity (CEC), soil reaction, electrical conductivity (EC), soil organic matter (SOM) content, and nutrient retention [16].

In this study organic residues generated within the homestead based integrated farming system were converted into biochar and physical and chemical properties of the produced biochar were assessed.

2. MATERIALS AND METHODS

2.1 Collection of Organic Residue

Organic residue produced within the premises of the Integrated Farming System Research, located in Karamana, Trivandrum, including coconut leaves, banana pseudostem, okra crop residues, teak leaves, and aquatic weeds namely

Eichhornia crassipes, *Limnocharis flava*, and *Colocasia esculenta*, which were found in the irrigation channels, were collected for the purpose of biochar production. The gathered materials were subjected to sun drying in an open environment for a period ranging from 3 to 5 days in order to eliminate the moisture present on the surface.

2.2 Production of Biochar

Biochar was generated through the utilization of the slow pyrolysis technique within a dual-barrel biochar kiln, equipped with a chimney for the expulsion of syngas. The internal barrel was responsible for holding the substrate, and in order to facilitate partial aeration, perforations were present at both the bottom and lid sections. Below the barrel, there was a designated fuel slot for the purpose of incineration. To monitor the temperature developed throughout the process, a digital infrared thermometer was employed [17].

2.3 Characterization of Biochar

The biochar derived from coconut leaves (CLB), banana pseudostem (BPB), crop residues (CRB), teak leaves (TLB), *Eichhornia crassipes* (EB), *Limnocharis flava* (LB), and *Colocasia esculenta* (CB) were pulverized and filtered through a 2mm sieve. The resulting samples were subjected to characterization using standard procedures. pH, electrical conductivity (EC) (1:20 (w/v)), cation exchange capacity (CEC), and the concentrations of nitrogen (N), phosphorus (P), and potassium (K) in the samples were determined using the protocols established by Jackson [18]. The estimation of N was carried out using the Kjeldahl steam distillation method, while the concentrations of P, K, and S in the biochars were analyzed after digestion with nitric-perchloric acid. The physical parameters viz., bulk density and water holding capacity and total organic carbon (TOC) content were determined using the procedure outlined by Piper [19].

2.4 Statistical Analysis

Data generated was analyzed using completely randomized design (CRD). The f values for the treatments were compared to the values in the table. If the effects were found to be significant, critical differences (CD) at a significance level of 5% were calculated to compare the means. For data analysis, the R-package grapesAgri1 was utilized [20].

3. RESULT AND DISCUSSION

3.1 Production of Biochar

The temperature of pyrolysis of bioresidues ranged 300 to 500 °C (Table 1). Higher temperature range of 450-500 °C was recorded for coconut leaves biochar and lowers 250-350°C for *Eichhornia crassipes* biochar. Banana pseudostem biochar required higher retention time of 90-120 minutes, while lower 30-50 minutes in *Eichhornia crassipes* biochar. A temperature range of 350-450°C was also recorded by Gopal et al. [21] for the production of biochar from coconut palm residues. [22] have reported that the pyrolysis temperature for biochar production generally ranges 300 to 1000 °C. But pyrolysis carried out at temperature range 300 to 700 °C yields more biochar [23]. Coconut leaf biochar recorded the higher recovery percentage of 46.53 per cent.

3.2 Physical Properties of Biochar

The range of bulk density observed for biochar was from 0.21 (Banana pseudostem biochar) to 0.52 (Teak leaves biochar) Mg m⁻³ as shown in Table 2. According to Brewer [24], biochar generally exhibits a lower bulk density, typically falling within the range of 0.2-0.5 g cm⁻³. It is important to acknowledge that the density may vary depending on the type of raw material used and the specific processes utilized in biochar production. The decrease in bulk density of biochar may be ascribed to the desiccation and carbonization of biomass, leading to an increase in pore volume and specific surface area [25].

Table 1. Production parameters and recovery percentage of biochar

Biochar	Temperature of pyrolysis (°C)	Residence time (min)	Recovery percentage (%)
TLB	400-450	45-60	34.57
CLB	450-500	60-90	46.53
BPB	350-400	90-120	26.10
CRB	350-450	60-90	32.70
EB	250-350	30-50	24.93
LB	300-400	30-60	27.46
CB	350-400	45-60	30.40

Table 2. Physical properties of biochar

Biochar	Bulk density (Mg m ⁻³)	Water holding capacity (%)
TLB	0.52	169.62
CLB	0.43	236.54
BPB	0.21	327.74
CRB	0.28	274.56
EB	0.37	252.65
LB	0.32	266.61
CB	0.41	228.09
SEm±	0.022	3.552
CD (0.05)	0.066	10.774

The findings showcased the remarkable ability of biochar to retain water. The biochar derived from banana pseudostem exhibited the highest water retention rate, measuring at 327.74%, followed by the biochar produced from *Limnocharis flava*, which recorded a water retention rate of 274.56% (Table 2). This disparity may be attributed to the significantly lower bulk density observed in the banana pseudostem biochar in comparison to the other samples. Water holding capacity depends on porosity of biochar's bulk volume [26].

3.3 Chemical Properties of Biochar

The chemical properties of produced biochar is given in Table 3. The biochars that were generated exhibited an alkaline characteristic, with their pH values ranging from 8.19 (*Colocasia esculenta* biochar) to 10.4 (Banana pseudostem biochar). During the pyrolysis process, the cations, namely potassium (K), calcium (Ca), silicon (Si), and magnesium (Mg), undergo a conversion into metal oxides, which are commonly referred to as ash. Subsequently, these metal oxides are blended with the biochar, resulting in the alkaline nature of the latter [27]. Additionally, the hydrolysis of salts containing alkaline metals has the capacity to render the biochar alkaline [28].

Wide variation in the electrical conductivity (EC) was observed among the different types of biochars. The EC of biochar is primarily dependent on the material used as feedstock. Notably, the teak leaves biochar exhibited a high EC value of 4.70 dS m⁻¹. The high electrical conductivity observed in the biochar can possibly be attributed to several factors. These factors include the presence of phosphates, silica, heavy metals, and sesquioxides, dominance of carbonates of alkali and alkaline earth metals, as well as the reduced amount of organic and inorganic nitrogen [29].

The biochar derived from banana pseudostem exhibited the highest CEC value, measuring 14.10 cmol (+) kg⁻¹. This can be attributed to the incomplete decomposition of cellulose during the carbonization process, which leads to the retention of oxygen-containing functional groups in the biochar [30]. Additionally, the amorphous structure of the graphene sheets within the biochar contributes to a larger surface area available for chemical reactions, thereby influencing the CEC of the biochar [31].

Biochar is known for its elevated carbon composition, predominantly consisting of carbon in an aromatic configuration. The presence of a condensed aromatic framework within biochar is responsible for its stability [32]. The total carbon content (TOC) of produced biochars exhibits variability, ranging from 42.20% (Teak leaves biochar) to 67.52% (Banana pseudostem biochar), which aligns with the outcomes obtained by Sorgonà et al. [33] and Nair et al. [34]. In comparison to combustion, the conversion of biomass to biochar effectively sequesters approximately 50% of the initial carbon [35].

The nutrient composition in biochar is subject to variation based on the selection of feedstock material. Primary and secondary nutrient content of produced biochar is given in Table 4. Banana pseudostem biochar has been found to possess high levels of nitrogen (1.24%), potassium (2.24%) and sulfur (0.33%) content, whereas biochar derived from *Limnocharis flava* exhibits elevated phosphorus content (0.77%). Biochar derived from the crop residue of okra exhibits notable calcium (0.57%) and magnesium (0.43%). Furthermore, biochar contains a significant quantity of trace elements (Table 5) and is capable of enriching the soil nutrient pool by acting as a source of both macro and micronutrient.

Table 3. Chemical properties of biochars

Biochar	pH	EC (dS m ⁻¹)	TOC (%)	CEC (cmol(+) kg ⁻¹)
TLB	8.46	4.70	42.20	11.37
CLB	9.95	3.86	50.87	11.80
BPB	10.40	3.60	67.52	14.10
CRB	9.16	4.10	59.61	13.00
EB	9.53	1.98	53.78	9.34
LB	8.83	2.87	63.80	12.70
CB	8.19	3.33	47.49	10.14
SEm±	0.193	0.271	1.091	0.238
CD (0.05)	0.585	0.823	3.249	0.722

Table 4. Macro nutrient content of biochar

Biochar	N (%)	P (%)	K (%)	Ca (%)	Mg (%)	S (%)
TLB	0.58	0.41	0.64	0.48	0.29	0.03
CLB	0.86	0.53	1.97	0.33	0.23	0.31
BPB	1.24	0.45	2.24	0.52	0.32	0.33
CRB	0.75	0.62	1.12	0.57	0.43	0.24
EB	0.67	0.31	0.79	0.27	0.24	0.11
LB	0.94	0.77	0.92	0.43	0.20	0.18
CB	0.37	0.28	1.04	0.36	0.19	0.16
SEm±	0.027	0.006	0.048	0.024	0.010	0.007
CD (0.05)	0.585	0.823	0.722	0.074	0.029	0.025

Table 5. Micro nutrient content of biochar

Biochar	Fe (mg kg ⁻¹)	Mn (mg kg ⁻¹)	Zn (mg kg ⁻¹)	Cu (mg kg ⁻¹)	B (mg kg ⁻¹)
TLB	1892.50	71.93	24.26	14.01	22.13
CLB	1776.11	94.86	41.69	7.10	6.26
BPB	1394.26	128.06	69.37	25.00	42.47
CRB	997.83	102.23	37.93	10.04	14.50
EB	1665.93	144.46	52.13	25.12	36.60
LB	1893.67	173.76	64.44	37.12	47.40
CB	2314.15	159.47	57.44	29.13	38.06
SEm±	4.302	6.231	1.731	0.585	0.766
CD (0.05)	13.129	18.915	5.416	1.773	2.323

4. CONCLUSION

There exists an excess in the production of organic waste due to the escalation of farming practices. The challenge of managing organic waste can be addressed by converting it into biochar, which transforms biomass into a carbonaceous substance that is abundant in nutrients. The physio-chemical characteristics of biochar are predominantly influenced by the original feedstock material. Previous studies have demonstrated the positive impact of applying biochar on soil properties and crop growth. The utilization of biochar within agricultural systems presents a potential alternative for augmenting the natural rates of carbon sequestration in soil, diminishing farm waste, and enhancing soil quality.

ACKNOWLEDGEMENTS

I extend my sincere thanks to Kerala Agricultural University for providing fund and facilities to carry out this research.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

1. Porichha GK, Hu Y, Rao KT, Xu CC. Crop residue management in India: Stubble burning vs. other utilizations including bioenergy. *Energies*. 2021;14(14):4281.
2. Venkatramanan V, Shah S, Rai AK, Prasad R. Nexus between crop residue burning,

- bioeconomy and sustainable development goals over north-western India. *Frontiers in Energy Research*. 2021 Jan 26;8: 614212.
3. Oni BA, Oziegbe O, Olawole OO. Significance of biochar application to the environment and economy. *Annals of Agricultural Sciences*. 2019 Dec 1;64(2): 222-36.
 4. Babu S, Singh R, Kumar S, Rathore SS, Yadav D, Yadav SK, Yadav V, Ansari MA, Das A, Rajanna GA, Wani OA. Biochar implications in cleaner agricultural production and environmental sustainability. *Environmental Science: Advances*. 2023;2(8):1042-59.
 5. Lehmann J. A handful of carbon. *Nature*. 2007 May 10;447(7141):143-4.
 6. Anjali T, Anand M, Akhilesh K, Madhuraj P, CS RK, Waran A. Physico-chemical Characterization of Biochar from Selected Ligno-cellulosic Biomass for The Sustainable Utilization. *International Journal of Applied Biology*. 2022 Dec 29; 6(2):186-212.
 7. Atkinson CJ, Fitzgerald JD, Hipps NA. Potential mechanisms for achieving agricultural benefits from biochar application to temperate soils: a review. *Plant and soil*. 2010 Dec;337:1-8.
 8. Shi S, Zhang Q, Lou Y, Du Z, Wang Q, Hu N, Wang Y, Gunina A, Song J. Soil organic and inorganic carbon sequestration by consecutive biochar application: Results from a decade field experiment. *Soil Use and Management*. 2021 Jan;37(1):95-103.
 9. Ding Y, Liu Y, Liu S, Li Z, Tan X, Huang X, Zeng G, Zhou L, Zheng B. Biochar to improve soil fertility. A review. *Agronomy for sustainable development*. 2016 Jun;36: 1-8.
 10. Pan D, Liu C, Yu H, Li F. A paddy field study of arsenic and cadmium pollution control by using iron-modified biochar and silica sol together. *Environmental Science and Pollution Research*. 2019 Aug 1;26: 24979-87.
 11. Ippolito JA, Spokas KA, Novak JM, Lentz RD, Cantrell KB. Biochar elemental composition and factors influencing nutrient retention. *Biochar for environmental management: Science, Technology and Implementation*. 2015 Feb 20;139.
 12. Xie T, Reddy KR, Wang C, Yargicoglu E, Spokas K. Characteristics and applications of biochar for environmental remediation: a review. *Critical Reviews in Environmental Science and Technology*. 2015 May 3; 45(9):939-69.
 13. Sakhiya AK, Anand A, Kaushal P. Production, activation, and applications of biochar in recent times. *Biochar*. 2020 Sep; 2:253-85.
 14. Banu MR, Rani B, Kavya SR, Nihala Jabin PP. Biochar: A Black Carbon for Sustainable Agriculture. *International Journal of Environment and Climate Change*. 2023 Apr 21;13(6):418-32.
 15. Blanco-Canqui H. Biochar and soil physical properties. *Soil Science Society of America Journal*. 2017 Jul;81(4):687-711.
 16. Sun Z, Hu Y, Shi L, Li G, Han J, Pang Z, Liu S, Chen Y, Jia B. Effects of biochar on soil chemical properties: A global meta-analysis of agricultural soil. *Plant, Soil and Environment*. 2022 Jun 21;68(6):272-89.
 17. Nagula S. Technology refinement for biochar production and evaluation of its effect on soil health and crop production. Ph.D. thesis. Kerala Agricultural University. 2017;185.
 18. Jackson ML. *Soil Chemical Analysis*. 2nd ed. Prentice Hall of India (Pvt) Ltd: New Delhi; 1973.
 19. Piper CS. *Soil and Plant Analysis*. Hans Publications: Bombay; 1966.
 20. Gopinath PP, Parsad R, Joseph B, Adarsh VS. grapesAgri1: collection of shiny apps for data analysis in agriculture. *Journal of Open Source Software*. 2021 Jul 18;6(63): 3437.
 21. Gopal M, Gupta A, Shahul Hameed K, Sathyaseelan N, Khadeejath Rajeela TH, Thomas GV. Biochars produced from coconut palm biomass residues can aid regenerative agriculture by improving soil properties and plant yield in humid tropics. *Biochar*. 2020 Jun;2:211-26.
 22. Xie T, Reddy KR, Wang C, Yargicoglu E, Spokas K. Characteristics and applications of biochar for environmental remediation: a review. *Critical Reviews in Environmental Science and Technology*. 2015 May 3; 45(9):939-69.
 23. Sakhiya AK, Anand A, Kaushal P. Production, activation, and applications of biochar in recent times. *Biochar*. 2020 Sep; 2:253-85.
 24. Brewer CE. *Biochar characterization and engineering*. Iowa State University; 2012.
 25. Hariz AM, Azlina WA, Fazly MM, Norziana ZZ, Ridzuan MM, Tosiah S, Ain AN. Local practices for production of rice husk biochar and coconut shell biochar:

- Production methods, product characteristics, nutrient and field water holding capacity. *Journal of Tropical Agriculture and Food Science*. 2015;43(1): 91-101.
26. Weber K, Quicker P. Properties of biochar. *Fuel*. 2018 Apr 1;217:240-61.
27. Novak JM, Busscher WJ, Laird DL, Ahmedna M, Watts DW, Niandou MA. Impact of biochar amendment on fertility of a southeastern coastal plain soil. *Soil science*. 2009 Feb 1;174(2):105-12.
28. Gaskin JW, Steiner C, Harris K, Das KC, Bibens B. Effect of low-temperature pyrolysis conditions on biochar for agricultural use. *Transactions of the ASABE*. 2008;51(6):2061-9.
29. Rajkumar R, Aggrading lateritic soil using biochar. Ph.D. thesis. Kerala Agricultural University. 2019;301.
30. Lee JW, Kidder M, Evans BR, Paik S, Buchanan lii AC, Garten CT, Brown RC. Characterization of biochars produced from corn stovers for soil amendment. *Environmental science & technology*. 2010 Oct 15;44(20):7970-4.
31. Kharel G, Sacko O, Feng X, Morris JR, Phillips CL, Trippe K, Kumar S, Lee JW. Biochar surface oxygenation by ozonization for super high cation exchange capacity. *ACS Sustainable Chemistry & Engineering*. 2019 Sep 4;7(19):16410-8.
32. Downie A, Crosky A, Munroe P. Physical properties of biochar. *Biochar for environmental management: Science and technology*. 2009;13.
33. Sorgonà A, Longo L, Proto AR, Cavalletti P, Cecchini M, Salvati L, Gallucci F, Colantoni A. Characterization of biochar and syngas obtained from pellets of grape vine and sun flower husk using a pyrolysis system. *Procedia-Social and Behavioral Sciences*. 2016 Jun 10;223:871-8.
34. Nair RR, Schaate A, Klepzig LF, Turcios AE, Lecinski J, Shamsuyeva M, Endres HJ, Papenbrock J, Behrens P, Weichgrebe D. Physico-chemical characterization of walnut shell biochar from uncontrolled pyrolysis in a garden oven and surface modification by ex-situ chemical magnetization. *Clean Technologies and Environmental Policy*. 2023 Apr 18:1-20.
35. Lehmann J, Gaunt J, Rondon M. Bio-char sequestration in terrestrial ecosystems—a review. *Mitigation and adaptation strategies for global change*. 2006 Mar;11: 403-27.

© 2023 Diya et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:

The peer review history for this paper can be accessed here:
<https://www.sdiarticle5.com/review-history/109065>